

Avesta FCW 2205-PW

Flux cored wire

Classifications

high-alloyed rutile

EN ISO 17633-A:

AWS A5.22:

T 22 9 3 N L P M21 1 ; T 22 9 3 N L P C 1 1

E2209T1-4 ; E2209T1-1

Characteristics and field of use

Avesta FCW 2205-PW is primarily designed for welding duplex stainless steels such as 2205. Avesta FCW 2205-PW has a stronger arc and a faster freezing slag compared to the 2D type. It is designed for all-round welding and can be used in all positions without changing the parameter settings. Weldability is excellent in the vertical-up and overhead welding positions. Avesta FCW 2205-PW should be welded using direct current positive polarity (DC+) with a recommended wire stick-out of 15 – 20 mm. The weldability of duplex steels is excellent, but the welding should be adapted to the base material, considering fluidity, joint design, heat input etc.

Corrosion resistance:

Very good resistance to pitting and stress corrosion cracking in chloride containing environments. PREN >35. Meets the corrosion test requirements per ASTM G48 Methods A, B and E (22°C).

Base materials

For welding steels such as					
Outokumpu	EN	ASTM	BS	NF	SS
2205	1.4462	S32205	318S13	Z3 CND 22-05 Az	2377

Typical analysis of all-weld metal (Wt-%)


C	Si	Mn	Cr	Ni	Mo	N
0.025	0.7	1.0	23.0	9.1	3.2	0.13

Ferrite 40 FN; WRC-92

Mechanical properties of all-weld metal

Heat Treatment	Yield strength 0.2%	Tensile strength	Elongation ($L_0=5d_0$)	Impact values in J CVN	
	MPa	MPa	%	+20°C:	-40°C:
untreated	600	800	27	80	55

Operating data

	Polarity = +	Shielding gas: Ar + 15 – 25% CO ₂ offers the best weldability, but 100% CO ₂ can also be used (voltage should be increased by 2V). Gas flow rate 20 – 25 l/min.
---	--------------	---

Dimensions (mm)	Amperage A
1.2	125-240